



Product Information Flyer

DESCRIPTION

CIMPERIAL HD 265Z is a premium water soluble “super lubricant” metal working fluid.

APPLICATION

CIMPERIAL HD 265Z was developed for use on carbon steels, high speed steels, high alloy steels, stainless steel, and tool steel. Should not be used on copper, copper alloys, brass, bronze or magnesium alloys. Designed for use in heavy-duty operations such as bearing, strut, and valve grinding.

FEATURES & BENEFITS

LUBRICITY:

CIMPERIAL HD 265Z contains a Patented Extreme Pressure (EP) additive which provides outstanding stock removal permitting high productivity increases. A series of extreme pressure lubricants are activated at various temperatures to permit high stock removals that are not possible with conventional water based fluids.

PRODUCTIVITY:

CIMPERIAL HD 265Z improves part quality, lowers wheel and tool usage. Lower fluid makeup rates equates to increases in machine uptime.

PROCESS IMPROVEMENTS:

CIMPERIAL HD 265Z reduces cycle times, resulting in longer wheel and tool life, while providing less horsepower required to make the part.

RECOMMENDED STARTING DILUTIONS

CIMPERIAL HD 265Z is to be mixed with water for use. Always add concentrate to water. Fluid may be more difficult to mix when water temperature is below 55°F. Add no other materials to the concentrate or mix unless approved by your CIMCOOL® District Manager.

Grinding	5% - 10%	(1:20 to 1:10)
Machining	5% - 10%	(1:20 to 1:10)

CONCENTRATION

Non-solvent Titration, Total Alkalinity or Refractometer can be used.

The Refractometer Factor is 0.8

A refractometer is only recommended for use in checking the concentration of a fresh charge. Multiply the scale reading obtained on your CIMCOOL® Refractometer by this factor to obtain the mix concentration in percent. Calibrate the refractometer so that it reads 0.0 with water before testing the sample mix. Remove gross contaminants from the sample mixes before testing.

TYPICAL PHYSICAL AND CHEMICAL PROPERTIES

Physical State: Liquid

Solubility in water: 100% miscible

Viscosity (SUS) @ 100°F: 600

pH Concentrate: NA

Total Chlorine/Chloride, wt%: 0.0/<50ppm

Silicones: Yes

Appearance and Odor: Clear/Chemical

Weight, lb/gal, 60°F (15.6 °C): 8.4

Flash Point /Sp.Gr./Boiling Point: SEE MSDS

pH Mix 5%, Typical Operating: 8.9

Total Sulfur, wt%: 13.0

HANDLING AND STORAGE

If frozen, product separates. Thaw completely at room temperature and stir thoroughly. Inside storage is recommended.

SAFETY DATA SHEET

Available at www.cimcool.com

For additional information refer to its OSHA MSDS, website or contact your local CIMCOOL TECHNICAL SPECIALIST OR DISTRICT MANAGER, or you may contact CIMCOOL® Technical Services at 1-513-458-8199.

Limitation of Liability: Under no circumstances, shall we or any affiliate of ours have any liability whatsoever for loss of use, or for any indirect or consequential damages. Minor formulation changes or normal variations in the manufacture of this product may cause slight variances in the data presented on this sheet.