# Houghto-Quench G

**General Purpose Accelerated Cold Quenching Oil** 

#### **DESCRIPTION**

Houghto-Quench G is a medium speed quenching oil suitable for use at temperatures up to 180°F (82°C). It is based upon specialty solvent refined base oil to minimize oxidation and ensure consistent performance under the most arduous of operating conditions. A carefully formulated additive package is incorporated into Houghto-Quench G to reduce the duration of the vapor blanket cooling stage and provide moderately accelerated quenching characteristics, together with excellent oxidation resistance and thermal stability.

### **APPLICATION**

The accelerated quenching characteristics provided by Houghto-Quench G enables the development of improved strength and hardness with minimum distortion in lower hardenability and low alloy steels, heavy sectioned components or steels of borderline hardenability.

Houghto-Quench G is suitable for use in all types of quenching installations including open quench tanks, sealed quench furnaces and continuous furnaces of the shaker hearth, cast link and mesh belt type. It is recommended particularly for applications where staining of components during quenching should be minimized.

## **DATA (TYPICAL VALUES)**

Kinematic Viscosity @ 100°F (37.8°C)	100 SUS (20.5 cSt)
Flash Point (minimum)	350°F (177°C)
Specific Gravity @ 60°F (15.6°C)	0.88
GMQS @ 80°F (26.7°C) (ASTM D-3520)	10 – 12 seconds

#### **FEATURES/ BENEFITS**

- Fast cooling rate in initial stage of quenching: Maximum metallurgical and physical properties
- Minimal drag-out of quenching oil: Less smoke and makeup required
- Excellent oxidation resistance and thermal stability: elimination for waste due to quench oil degradation

#### **HEALTH AND SAFETY**

Refer to MSDS for proper handling and disposal. Please note that the MSDS includes handling, health and disposal information which should be passed on to your employees, and to anyone else who comes in contact with our product. Additional advice can also be obtained from your local Houghton representative.

NOTE: Read and understand all precautions on container labels before using this product.

Date I version Code



Houghton International Inc. Madison and Van Buren Aves. P. O. Box 930 Valley Forge, PA 19482-0930 Phone: 610-666-4000 Fax: 610-666-0174 info@houghtonintl.com www.houghtonintl.com

This document contains information based on data that is believed to be correct. However, the product may not be applicable to all uses and operating environments. No warranty or guarantee is expressed or implied.

## **COOLING CURVE ANALYSIS**

By ivf quenchotest

#### **Houghto-Quench G**

Date:

3/12/2010

**Test Parameters:** 

Sample Size - 1 liter

Bath Temp.-


140° F

Probe -IFHT Std. Inconel 600

Agitation-

None

Sample #1- Houghto-Quench G



#### **COMMENTS:**

Tested according to Houghton International laboratory procedure Q03.